

GWC DECORATIVE CONCRETE PROCESS AND MATERIAL DESCRIPTIONS

EXCAVATION

- ALL SITES FOR CONCRETE WORK WILL BE EXCAVATED DOWN TO FIRM SOIL SO A MINIMUM OF 2" OF COMPACTED GRAVEL CAN BE PLACED UNDER A MINIMUM OF 4" OF CONCRETE.

CONCRETE

- CONCRETE IS PLACED AT A MINIMUM OF 4" THICK.
- CONCRETE IS A 3500PSI MIX DESIGN

REBAR

- REBAR IS PLACED 3' ON CENTER THRU OUT ALL CONCRETE UNLESS OTHERWISE SPECIFIED BY SPECIFIC CODES OR ENGINEERS REQUIREMENTS.

CONCRETE FINISHES AVAILABLE

- BROOM FINISH : TEXTURE OF SURFACE WITH A BROOM LEAVING THE PROFILE OF A RECORD ACROSS THE SURFACE OF THE CONCRETE
- EXPOSED AGGREGATE FINISH: SURFACE OF CONCRETE WASHED OFF TO EXPOSE BEAUTIFUL AGGREGATE IN CONCRETE
- SAND FINISH: SURFACE OF CONCRETE IS WASHED OFF TO EXPOSE THE SAND JUST BELOW THE SURFACE. LOOKS AND FEELS LIKE BEACH SAND.
- STAMPED CONCRETE FINISH: CONCRETE IS PLACED. WHILE CONCRETE IS WET COLOR IS CAST ON AND TROWELLED INTO SURFACE CHANGING UPPER 3/8" OF CONCRETE SURFACE. A RELEASE POWDER(ALSO THE SECOND HIGHLIGHT COLOR) IS PLACED. THE SURFACE IS THEN IMPRINTED (STAMPED) IN A PATTERN CHOSEN BY CUSTOMER.

SEALER

- AFTER CONCRETE IS CURED AN ACRYLIC SEALER IS APPLIED TO THE SURFACE OF THE CONCRETE. THIS IS APPLIED TO EXPOSED AGGREGATE, SAND FINISH AND STAMPED CONCRETE.

DECORATIVE CONCRETE MAINTANACE

- DECORATIVE CONCRETE NEEDS TO BE PRESSURE WASHED AND RESEALED EVERY TWO YEARS AFTER THE FIRST 2 CONSECUTIVE ANNUAL APPLICATIONS.